

# Technical Data Sheet

## MEDI-GEHR PEEK MG®

PLASTICS ENGINEERED BY  

 GEHR

### I. Physical Properties<sup>1)</sup>

	Test method	Unit	Value
1. Specific gravity ( $\rho$ )	ISO 1183	g/cm <sup>3</sup>	1,32
2. Water absorption <sup>9)</sup>	ISO 62	%	0,4
3. Humidity absorption <sup>9)</sup>			0,07
4a. Maximum permissible service temp <sup>9)</sup>	UL746B	°C	260
4b. Lower permissible service temp <sup>9)</sup>			-40

### II. Mechanical Properties

	Test method	Unit	Value
1. Tensile strength at yield ( $\sigma_s$ )	ISO 527	MPa	115
2. Elongation at yield. ( $\epsilon_s$ )		%	7
3. Tensile strength at break ( $\sigma_R$ )		MPa	67
4. Elongation at break ( $\epsilon_R$ )		%	16
5. Impact strength ( $a_n$ )	ISO 179	kJ/m <sup>2</sup>	n.b.
6. Notch impact strength ( $a_k$ ) <sup>9)</sup>			4
7. Ball indentation ( $H_k$ )/Rockwell hardness <sup>9)</sup>	ISO 2039	MPa	250/M 99
8. Shore-D	ISO 868		90
9. Flexural strength ( $\sigma_B$ 3,5 %) <sup>9)</sup>	ISO 178	MPa	170
10. Modulus of elasticity ( $E_t$ )	ISO 527		4210

### III. Thermal Properties<sup>9)</sup>

	Test method	Unit	Value
1. Vicat-softening point. VST/B/50	ISO 306	°C	250
VST/A/50			-
2. Heat deflection temperature. HDT/B	ISO 75	°C	240
HDT/A			158
3. Coef. of linear thermal expansion ( $\alpha$ )	ISO 11359	K <sup>-1</sup> *10 <sup>-4</sup>	0,47
4. Thermal conductivity at 20 °C ( $\lambda$ )	ISO 22007-4	W/(m*K)	0,25
5. Glass transition temperature. (T <sub>g</sub> )	ISO 3146	°C	143
6. Melting temperature (T <sub>m</sub> )			340

### IV. Electrical Properties

	Test method	Unit	Value
1. Volume resistivity ( $\rho_D$ ) <sup>8)</sup>	IEC 60093	Ω*cm	≥ 10 <sup>13</sup>
2. Surface resistivity (R <sub>o</sub> ) <sup>8)</sup>		Ω	≥ 10 <sup>13</sup>
3. Dielectric constant at 1MHz ( $\epsilon_r$ ) <sup>9)</sup>	IEC 60250	-	3,2
4. Dielectric loss factor at 1 MHz (tanδ) <sup>9)</sup>		-	0,003
5. Dielectric strength <sup>9)</sup>	IEC 60243-1	kV/mm	16
6. Tracking resistance <sup>9)</sup>	IEC 60112	V	CTI 125

### V. Additional Data

	Test method	Unit	Value
1. Bondability	-	-	+
2. Physiological.indifference <sup>5)</sup> according	EEC FDA	- -	+
3. Biocompatibility	ISO 10993 USP	-1, -5, -12, -18 class VI	+
4. Flammability <sup>9)</sup>			+
5. Limiting Oxygen Index (LOI) <sup>9)</sup>	ASTM D2863	%	35
6. UV stabilisation <sup>6)</sup>	-	-	o

1) The physical data contained in this table are typical values and reflect the current state of our knowledge. The data are arithmetic average values which are tested by test specimens made out of rods (ø 40-60 mm). These has to be understood as guidelines, and shall not be used for specification purposes for finished parts. Missing data are completed by data of the raw materials.

5) Physiological indifferences are valid for nature coloured materials on the raw material side. There are also approvals for our semi-finished products available or in preparation. Please check this separately with us. 6) valid for nature coloured materials. An additional UV protection can be taken over by special pigments e.g. carbon black. 7) Test results without UL registration 8) Data are only valid for natural colours

9) Data taken from raw material

+ = yes o = limited - = no/no data available

n.b. = no break